

Aluminum (4000 Series)

Strips



Material Designation	Chemical Composition (%)	Alloys																					
4000 Series	<table><tr><td>Al</td><td>94.8 - 98.6</td></tr><tr><td>Cu</td><td>0.30 Max</td></tr><tr><td>Fe</td><td>0.80 Max</td></tr><tr><td>Mg</td><td>0.05 Max</td></tr><tr><td>Mn</td><td>0.05 Max</td></tr><tr><td>Si</td><td>4.5 - 6.0</td></tr><tr><td>Zn</td><td>0.10 Max</td></tr></table>	Al	94.8 - 98.6	Cu	0.30 Max	Fe	0.80 Max	Mg	0.05 Max	Mn	0.05 Max	Si	4.5 - 6.0	Zn	0.10 Max	<table><tr><td>4004</td></tr><tr><td>4006</td></tr><tr><td>4007</td></tr><tr><td>4045</td></tr><tr><td>4047</td></tr><tr><td>4104</td></tr><tr><td>4343</td></tr></table>	4004	4006	4007	4045	4047	4104	4343
Al	94.8 - 98.6																						
Cu	0.30 Max																						
Fe	0.80 Max																						
Mg	0.05 Max																						
Mn	0.05 Max																						
Si	4.5 - 6.0																						
Zn	0.10 Max																						
4004																							
4006																							
4007																							
4045																							
4047																							
4104																							
4343																							

Specification		Applications
Thickness	0.05 - 6 mm	Architectural Appliance Wire Industry Construction Industry Automotive Industry Radiators Heat Exchangers
Width	12 – 2200 mm	
Length	-	
Inner Diameter	100, 200, 250, 300, 400, 500, 600 mm	
Outer Diameter	2500 mm Max.	
Tolerances	According to DIN, EN, ASME	
Elongation	0.5 - 5 %	
Tensile Strength	100 - 220 Mpa	
Yield Strength	45 - 120 Mpa	

Description

The 4000 series of alloys contain quite high silicon contents. The alloys offer good corrosion resistance and moderate strength. They are popular for a variety of welding wire and brazing wire applications. Their uses include sheet, forgings and welding and brazing products.

Value Proposition

- Competitive Pricing
- Flexible LME price fixation
- Product Customization
- Quality Assurance
- Committed to deliveries
- Standard export pallet packing

This data is general technical specification; Binding technical specifications will be as per agreement.