

Copper - ETP

Tubes



Material Designation		Chemical Composition (%)		Applications
ASTM	C11000	Cu	99.90 (Min.)	Solar Panels Heat Exchangers Refrigeration Industry Defense & Railways Electrical & Electronic Industry
JIS	C1100			
INDIAN	Cu-ETP	O2	0.04 (Max.)	
EN	CW004A			
BS	C101			

Specification		Shapes
O.D	1.0 - 80 mm	Round
Thickness	0.10 - 8.0 mm	Square
Length	0.50 – 12000 mm	Rectangle
Temper	O , 1/4H , 1/2H , 3/4H , H , EH , SH	Hexagonal

Description
<p>Electrolytic-Tough-Pitch (ETP) is the most common copper with a minimum conductivity rating of 100% IACS and is required to be 99.9% pure. It has 0.02% to 0.04% oxygen content. ETP Copper has an extremely wide range of applications based on its conductivity, corrosion resistance, workability, and beauty.</p>

Value Proposition
<ul style="list-style-type: none"> ● Competitive Pricing ● Flexible LME price fixation ● Product Customization ● Quality Assurance ● Committed to deliveries ● Standard export pallet packing

This data is general technical specification; Binding technical specifications will be as per agreement.